



TMQ SPECIFICATION

Parameters	Guaranteed value	Typical results	Test Method
Appearance	yellowish brown pastilles	yellowish brown pastilles	MM.02.001
Softening point, °C min - max	85.0 – 100.0	93-94	DIN/ISO 4625
Heat loss (2g/2h/105 °C) max	0,3	0.2	ASTM D 4571
Ash, % max	0.2	0.05	ASTM D 4574

If you'd like to have other parameters to be specified please contact us.